



TSAU0520
SEALER A 520

Descriptive notes Clear transparent polyurethane sealer suitable for exotic wood rich of oily substances and for Rosewood. The sealer should be applied at least n ° 3 coats.

MAIN PROPERTIES

Wetting Effect	Medium	Elasticity	Medium
Insulating Effect	High	Sanding	Sufficient
Improving Adhesion	High		

USAGE

Suitable for	Panelling	M.D.F.	Furniture				
Method of application	spray	Cloth	Brush.				

PREPARATION OF THE PRODUCT

	Code	%	Descriptive notes
Recommended thinner			
Other thinners			
Recommended hardener	INUR0520	100	
Other hardeners			

CHEMICAL-PHYSICAL CHARACTERISTICS		APPLICATION CHARACTERISTICS		DRYING	
Specific gravity (kg/l) ±0.03	0,91	N° of hands	1→3	Overcoatings (h)	3÷12
Solids Content (%) ±1	12	Qty. per coat (g/m²)	30÷60	Sanded (h)	3
Viscosity DIN (20°C) 3	18"±20"			Stackable (h)	8
Pot-Life at 20°C (h)	>4			Dust free (min)	15
				Touch dry (min)	45

Additional information: ☐ Sanding and clean thoroughly the support using grit sand papers 100 ÷ 160.

Overcoatings with Topcoat type	Polyurethane	Acrylic	Polyester	
---------------------------------------	--------------	---------	-----------	--

WARNING Our data sheets are drawn up on the basis of average results of our trials. However our tech tips are given in good faith but without guarantee. In fact, several media, conditions of application, plant and dilutions are an integral part of the final result and often beyond our control. The user must try the products supplied to test whether suitable to your needs. For our part we guarantee the continuity of the chemical-physical characteristics.
Warning: it is the user's responsibility to provide that the application is in properly ventilated environment hygienic and in accordance with standards and accident prevention regulations currently in force.

Revision n° 7 Revision Date 13/09/2017

Printed: 13/09/2017